

Appl. No. 10/765,660
Docket No. H1799-00216
Reply to Office Action of January 26, 2005

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A capillary structure for a heat transfer device comprising:

a plurality of particles joined together by a brazing compound comprising about sixty-five percent weight copper and thirty-five percent weight gold such that fillets of said brazing compound are formed between adjacent ones of said plurality of particles so as to form a network of capillary passageways between said particles wherein at least one vapor vent is defined through said capillary structure.
2. (Original) A capillary structure according to claim 1 wherein said plurality of particles comprise a first melting temperature and said brazing compound comprises a second melting temperature that is lower than said first melting temperature.
3. - 4. (Canceled)
5. (Currently Amended) A capillary structure according to claim 1 wherein said plurality of [meta] particles are selected from the group consisting of

BEST AVAILABLE COPY

Appl. No. 10/765,660
Docket No. H1799-00216
Reply to Office Action of January 26, 2005

carbon, tungsten, copper, aluminum, magnesium, nickel, gold, silver, aluminum oxide, and beryllium oxide.

6. (Currently Amended) A capillary structure according to claim 1 wherein said plurality of [meta] particles comprise a shape selected from the group consisting of spherical, oblate spheroid, prolate spheroid, ellipsoid, polygonal, and filament.

7. (Currently Amended) A capillary structure according to claim 1 wherein said plurality of [meta] particles comprise at least one of copper spheres and oblate copper spheroids having a melting point of about one thousand eighty-three °C.

8. (Currently Amended) A capillary structure according to claim 1 [3] wherein said brazing compound comprises six percent by weight of a finely divided copper/gold [brazing compound].

9. (Currently Amended) A capillary structure according to claim 1 [3] wherein said brazing compound is present in the range from about two percent to about ten percent by weight.

Appl. No. 10/765,660
Docket No. H1799-00216
Reply to Office Action of January 26, 2005

10. (Currently Amended) A capillary structure according to claim 1 [3] wherein said plurality of [meta] particles comprise copper powder comprising particles sized in a range from about twenty mesh to about two-hundred mesh.

11. – 14. (Canceled)

15. (Currently Amended) A capillary structure for a heat transfer device comprising:

a plurality of particles joined together by a brazing compound comprising about sixty-five percent weight copper and thirty-five percent weight gold such that fillets of said brazing compound are formed between adjacent ones of said plurality of particles so as to form a network of capillary passageways between said particles wherein a plurality of vapor vents are defined through said capillary structure.

16. (Original) A capillary structure according to claim 15 wherein said vapor vents comprise a cross-sectional profile selected from the group consisting of cylindrical, conical, frustoconical, triangular, pyramidal, rectangular, rhomboidal, pentagonal, hexagonal, octagonal, polygonal and curved.

17. (Currently Amended) A heat pipe comprising:

Appl. No. 10/765,660
Docket No. H1799-00216
Reply to Office Action of January 26, 2005

a hermetically sealed and partially evacuated enclosure, said enclosure comprising internal surfaces;

a wick disposed on at least one of said internal surfaces and comprising a plurality of particles joined together by a brazing compound comprising about sixty-five percent weight copper and thirty-five percent weight gold such that fillets of said brazing compound are formed between adjacent ones of said plurality of particles so as to form a network of capillary passageways between said particles wherein at least one vapor vent is defined through said capillary structure; and

a two-phase fluid at least partially disposed within a portion of said wick.

18. (Original) A heat pipe according to claim 17 wherein said plurality of particles comprise a first melting temperature and said brazing compound comprises a second melting temperature that is lower than said first melting temperature.

19. – 20. (Canceled)

21. (Currently Amended) A heat pipe according to claim 17 wherein said plurality of [meta] particles are selected from the group consisting of

Appl. No. 10/765,660
Docket No. H1799-00216
Reply to Office Action of January 26, 2005

carbon, tungsten, copper, aluminum, magnesium, nickel, gold, silver, aluminum oxide, and beryllium oxide.

22. (Currently Amended) A heat pipe according to claim 17 wherein said plurality of [meta] particles comprise a shape selected from the group consisting of spherical, oblate spheroid, prolate spheroid, polygonal, and filament.

23. (Currently Amended) A heat pipe according to claim 17 wherein said plurality of [meta] particles comprise at least one of copper spheres and oblate copper spheroids having a melting point of about 1083°C.

24. (Currently Amended) A heat pipe ~~according to claim 17~~ wherein ~~said brazing compound comprises~~ comprising:

a hermetically sealed and partially evacuated enclosure, said enclosure comprising internal surfaces;

a wick disposed on at least one of said internal surfaces and comprising a plurality of particles joined together by a brazing compound comprising six percent by weight of a finely divided copper/gold brazing compound such that fillets of said brazing compound are formed between adjacent ones of said plurality of particles so as to form a network of capillary

Appl. No. 10/765,660
Docket No. H1799-00216
Reply to Office Action of January 26, 2005

passageways between said particles wherein at least one vapor vent is defined through said capillary structure; and
a two-phase fluid at least partially disposed within a portion of said wick.

25. (Currently Amended) A heat pipe according to claim 17 wherein said brazing compound is present in the range from about two percent to about ten percent by weight.

26. (Currently Amended) A heat pipe according to claim 17 wherein said plurality of [meta] particles comprise copper powder comprising particles size in a range from about twenty mesh to about two-hundred mesh.

27. – 30.

31. (Original) A heat pipe comprising a sealed and partially evacuated tubular enclosure having an internal surface covered by a brazed wick comprising a plurality of copper particles joined together by a brazing compound comprising about sixty-five percent weight copper and thirty-five percent weight gold such that fillets of said brazing compound are formed between adjacent ones of said plurality of particles so as to form a network of capillary passageways between said particles and including a plurality of vapor vents defined through said wick; and

Appl. No. 10/765,660
Docket No. H1799-00216
Reply to Office Action of January 26, 2005

a working fluid disposed within said tubular enclosure.

32. -58. (Canceled)

59. (New Claim) A heat pipe comprising:

a hermetically sealed and partially evacuated enclosure, said enclosure comprising internal surfaces;

a wick disposed on at least one of said internal surfaces and comprising a plurality of aluminum and magnesium particles joined together by an aluminum/magnesium intermetallic alloy brazing compound such that fillets of said brazing compound are formed between adjacent ones of said plurality of particles so as to form a network of capillary passageways between said particles wherein at least one vapor vent is defined through said capillary structure; and

a two-phase fluid at least partially disposed within a portion of said wick.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.